



#75AF BULLDOG® HEAVY DUTY FLASHING CEMENT

DESCRIPTION

A heavy trowel consistency roofing mastic blended from high grade asphalt, petroleum spirits, mineral fillers and/or other stabilizers. Resists running or sagging at high temperatures. It has a tough outside shell but remains soft and pliable underneath. Consistency adjusted for seasonal use.

SPECIFICATIONS: ASTM D 4586, Type I, Class I Federal Specification SS-C-153 Type 1 (Except Non-Asbestos)

USES

Especially prepared for application to vertical surfaces. Useful as all-purpose roof cement for repairs of cracks, splits, and blisters on asphalt roofs. Can be used on metal surfaces. Primarily used to install, maintain, and repair flashings around parapet walls, skylights, vents, chimneys, ducts, flues, etc. Can be used on masonry surfaces. It is suggested that surfaces be primed with BULLDOG Asphalt Primer prior to application of cement. Effective in stopping leaks.

METHODS AND RATE OF APPLICATION

Use a trowel to apply to clean, dry surface. Re-nail loose ends and boards. Apply approximately 1/8 inch (3.2 mm.) thickness. One gallon (3.78 liters) will cover 13 square feet (1.2 square meters). For repairing cracks, splits, and blisters on built-up roofing use in conjunction with BULLDOG Asphalt Saturated Cotton Fabric or Polyester Fabric. **COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.**

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
5 Gallon Pail	46 POUNDS
1 Gallon Pail (6 to a Carton)	56 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight.....	79.0
Volatile Solvent, % by Weight.....	21.0
Mineral Filler and/or other Stabilizers, % by Weight.....	19.0
Asphalt Solids, % by Volume.....	61.0
Water Content, % by Volume.....	0.05
Net Weight Per Gallon.....	8.7
Dry Film Thickness Without Absorption Applied at Rate of 13 Square Feet Per Gallon.....	.77 Mils
Dry Time @ Recommended Rate of Application.....	3 Days - Outside Shell
Service Temperature	-30°F to +150°F
Behavior @ 60°C., ASTM D 4586.....	No Sagging, No Blistering
Behavior @ 0°C., ASTM D 4586	No Cracking, No Separation
Flash Point, in Degrees F, C.C., ASTM D 93	104 Minimum
Condition in Container	Homogeneous
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
196 WEST 5TH ST
P.O. BOX 58
BAYONNE, NJ 07002
PHONE(201) 339-0855
FAX (201) 339-8320
www.palmerasphalt.com