



SPECIFICATION DATA

1. Product Name

Versi-Foam® Systems 9, 15 and 50 Class I Slow Rise Disposable Foam Kits

2. Manufacturer

RHH Foam Systems, Inc.
 5500 South Westridge Drive | New Berlin, WI 53151
 Phone: 1-800-657-0702 | 262-754-8088
 Fax: 262-754-8089
 Email: sales@rhhfoamsystems.com
 Web: www.rhhfoamsystems.com



3. Product Description

Versi-Foam® Systems 9, 15, and 50 Class I Slow Rise are disposable, closed-cell, low-pressure spray foam kits consisting of two chemical components (Component A: isocyanate and Component B: polyol blend), patented U-Control dispensing gun, ten multi-purpose mixing nozzles, nitrile gloves, and packet of petroleum jelly. These systems contain a flame retardant formula, meeting requirements of ASTM E-84 as a Class I product. They do not require any external power source.

4. Technical Data

Versi-Foam® Systems 9, 15, and 50 Class I Slow Rise have the following physical properties:

DENSITY (ASTM D1622):

Free Rise	1.75 lb/f ³
In Place	2.0 lb/f ³

R FACTOR at 1" thickness (ASTM C518):

6.7

COMPRESSIVE STRENGTH (ASTM D1621):

13.8 psi (parallel)

CLOSED CELL CONTENT (ASTM D2856):

>95%

DIMENSIONAL STABILITY (ASTM D2126):

% Volume Change, 158°F, 100 RH, 7 days	2.01
% Volume Change, -60°F, 7 days	-0.42

TEMPERATURE TOLERANCE:

High Temperature Tolerance	250° F
Low Temperature Tolerance	-250° F

AIR BARRIER PROPERTIES at 75 Pa (ASTM E283):

0.005 L/s/m²

PERM RATING at 1" / at 3" (ASTM E96):

3.70 Perms / 1.83 Perms

TENSILE STRENGTH (ASTM D1623):

36.14 psi

FLAMESPREAD at 2" thickness (ASTM E84):

20

SMOKE DEVELOPED at 2" thickness (ASTM E84):

300

TACK FREE TIME:

2 minutes

RISE TIME:

2 minutes

YIELD:

System 9 Class I Slow Rise	9 f ³ 108 f ² @ 1" thick
System 15 Class I Slow Rise	16.5 f ³ 200 f ² @ 1" thick
System 50 Class I Slow Rise	50 f ³ 600 f ² @ 1" thick

- Versi-Foam® products do not contain any CFC's, Penta-BDE's, VOC's, or Urea-Formaldehyde.
- Published yields are theoretical and vary based on several factors, including ambient conditions and specific application.
- Always use recommended personal protective equipment when using polyurethane foam products. Refer to the Material Safety Data Sheet for additional information on safe use and handling of Versi-Foam® Systems.