



#85 BULLDOG® Q.D. PRIMER

DESCRIPTION

BULLDOG Q.D. Primer is a rapid drying special heavy bodied asphalt material which will dry to touch 3-4 hours and will cure in 24 hours (depending upon thickness of film and outside temperature). Meets ASTM D 41 Type II

USES

Use BULLDOG Q.D. Primer for priming concrete, asphalt and metal surfaces before the application of other BULLDOG Dampproofing and Waterproofing compounds and systems. Use as a quick dry primer to create a better bond between the surface applied to and compatible materials. THIS PRODUCT IS FOR EXTERIOR USE ONLY.

METHODS AND RATE OF APPLICATION

Apply BULLDOG Q.D. Primer to clean, dry surface by brush, spray, or squeegee at rate of 100 square feet per gallon (.4 liters per M²). Rate of application may vary due to porosity of substrate. DO NOT THIN. COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING. EMPTY CONTENTS BEFORE DISPOSING OF PAIL AND SPRAY CAN.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
12 - 14 oz Spray Cans	11 POUNDS
5 Gallon Pail	41 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight.....	63.0
Volatile Solvent, % by Weight.....	37.0
Asphalt Solids, % by Volume.....	60.0
Water Content, % by Volume.....	0.5
Net Weight Per Gallon, Pounds.....	7.6
Dry Film Thickness Without Absorption Applied at Rate of 100 Square Feet Per Gallon.....	8 Mils
Dry Time @ Recommended Rate of Application.....	3-4 Hrs. Touch, 24 Hrs. Hard
Service Temperature.....	-30°F to +160°F
Flash Point, in Degrees F., C.C., ASTM D 93.....	104
Condition in Container.....	Homogeneous, Slight Stirring Required
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES. The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
 196 WEST 5TH ST
 P.O. BOX 58
 BAYONNE, NJ 07002
 PHONE (201) 339-0855
 FAX (201) 339-8320
www.palmerasphalt.com