

Styrofoam™ Brand Highload 100 Extruded Polystyrene Foam Insulation

Subfloor Thermal Insulation for Low-Temperature Applications
U.S. HFC Regulation Compliant Formulation

OVERVIEW

Description

DuPont™ Styrofoam™ Brand Highload 100 Extruded Polystyrene (XPS) Insulation is a closed-cell foam insulation designed for demanding applications such as low-temperature (freezer floor) applications, highways, airport runways, bridge abutments, parking decks, utility lines, and ice rinks. With a compressive strength of 100 psi (690 kPa), it offers exceptional moisture resistance and R-value retention.

Styrofoam™ Brand Highload Insulation products are engineered to resist compressive creep and fatigue, ensuring sustained compressive strength over time. Like all Styrofoam™ Brand insulation products, **Highload 100 XPS Insulation** is known for its durability, versatility, and reusability, making it a preferred choice for a wide range of high-load applications.

Features and Benefits

- **Highly Moisture Resistant:** Superior resistance to water absorption, water vapor transmission and freeze thaw cycling
- **Long-Term Compressive Strength:** Resist compressive creep and fatigue

Sustainable Solutions

- Styrofoam™ Brand Highload XPS Insulation uses BluEdge™ technology. Styrofoam™ Brand Highload Insulation is designed to be compliant with U.S. state HFC regulations where sold. It uses enhanced level of sustainable blowing agents, and BluEdge™ flame retardant technology. It is hydrochlorofluorocarbon (HCFC) free with zero ozone depletion potential and is reusable in many applications.



Applications

Styrofoam™ Brand Highload 100 XPS Insulation is an ideal solution for a variety of high-load applications:

- Protected Membrane Roofs (PMR)
- Green Roof Applications
- Blue Roof Applications
- Geotechnical heavy load-bearing structures (airport runways, highways, helicopter landing pads, bridge abutments, parking decks)
- Conventional Roofs and single-ply membrane
- Below Grade foundation, floor, and wall Insulation

Warranty

- Styrofoam™ Brand Insulation is backed by a 50-year thermal limited warranty on products 1.5 inches and greater. For thickness less than 1.5 inches, other warranties may apply. For additional warranty information please visit building.dupont.com or contact your DuPont representative.

Standard Sizes

Standard Sizes for DuPont™ Styrofoam™ Brand Highload 100 XPS Insulation

Thickness	Width	Length	R-Value	Edge Treatment
1.5 in.	2 ft.	8 ft.	7.5	Square Edge
2 in.	2 ft.	8 ft.	10	Square Edge
3 in.	2 ft.	8 ft.	15.0	Square Edge

Note: Please be advised that additional sizes may be available. Availability of all sizes varies by region and is subject to change. For further information, please contact your local DuPont Sales Representative or call us at 1-866-338-7668.

TESTING AND CODE COMPLIANCE

Styrofoam™ Brand Highload 100 XPS Insulation exhibits the properties and characteristics indicated in the table below when tested as represented. Review all instructions and (Material) Safety Data Sheet ((M)SDS) before use. Please contact DuPont at 1-833-338-7668 when additional guidance is required for writing specifications that include this product.

TEST METHOD	TEST TITLE	PROPERTY	RESULTS
FIRE			
UL 723	Test Method for Surface Burning Characteristics of Building Materials	Surface Burning Characteristics	Flame Spread ≤ 25 Smoke Developed ≤ 450
THERMAL			
ASTM C518	Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus	Thermal Resistance per inch, @ 75°F mean temp. ¹	5.0 ft ² ·h·°F/Btu, R-value, min.
ASTM D696	Standard Test Method for Coefficient of Linear Thermal Expansion of Plastics Between -30°C and + 30°C with a Vitreous Silica Dilatometer	Coefficient of Linear Thermal Expansion	3.5 x 10-5 in/in·°F
ASTM D2126	Standard Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging	Change in Dimensions	2.0 % change, max.
STRENGTH			
ASTM D1621	Standard Test Method for Compressive Properties of Rigid Cellular Plastics	Compressive Strength ²	100 psi, min.
ASTM D1622	Standard Test Method for Compressive Properties of Rigid Cellular Plastics	Compressive Modulus (typical)	3,700 psi
ASTM C203	Standard Test Methods for Breaking Load and Flexural Properties of Block-Type Thermal Insulation	Flexural Strength	100 psi, min
WATER			
ASTM C272	Standard Test Method for Water Absorption of Core Materials for Sandwich Construction	Water Absorption	0.1 % by volume, max.
ASTM E96	Standard Test Methods for Gravimetric Determination of Water Vapor Transmission Rate of Materials	Water Vapor Permeance ³	0.8 perm, max.

¹Values are consistent with the criteria of ASTM C578 and the requirements of the FTC R-value rule (16 CFR Part 460). R means resistance to heat flow. The higher the R-value, the greater the insulating power.

²Vertical compressive strength is measured at 5% deformation or yield, whichever occurs first. Since Styrofoam insulations are visco-elastic, design safety factors are needed to limit long-term creep: 3:1 for static loads is suggested. For dynamic loads, call 18665832583.

³Based on 1" thickness.

CODE COMPLIANCE

Styrofoam™ Brand Highload 100 XPS Insulation complies with the following codes:

CODE	DESCRIPTION
US Product Listings & Verifications	Factory Mutual Approved International Residential Code (IRC) and International Building Code (IBC); see ICC-ES ESR-4755 Underwriters Laboratories, Inc. (UL) Classified, see Classification Certificate D-369
Regional Code Listings & Reports	California Std. Reg. #CA T1535

HANDLING

Cleanup & Disposal

- Dispose of any residual DuPont product, coated debris, or solvent in accordance with applicable federal, state, and local government regulations.

Product Limitations

- Building and/or construction practices unrelated to building materials could greatly affect moisture and the potential for mold formation. No material supplier including DuPont can give assurance that mold will not develop in any specific system.

- Styrofoam™ Brand XPS Insulation is made of extruded polystyrene (XPS) and can be recycled at facilities that recycle XPS materials. Please check recycling facilities in your area to ensure they can recycle XPS Insulation.

Handling & Use

- Before installation, substrate must be clean, dry, smooth and free from oil, grease, rust, frost and snow. Since dust would impair the performance of adhesives and finishes, dusty surfaces should be brushed off before products are applied.
- Do not leave Styrofoam™ Brand XPS exposed to direct sunlight for more than 90 days. Consult a DuPont representative if exposure is expected to be longer than 90 days. Prolonged exposure to ultraviolet radiation may cause the surface of Styrofoam™ Brand XPS to become faded and dusty. The surface degradation will have no measurable effect on the insulating value of the foam unless the deterioration is allowed to continue until foam thickness is lost.
- Use gloves to protect from mechanical injury.

Life & Storage

- In order to prevent buildup of combustible vapors, do not store large quantities of this product in unventilated spaces. Transport bulk shipments of this product in ventilated vehicles. During shipment, storage, installation and use, this material should not be exposed to flame or other ignition sources.

When stored outdoors, keep insulation boards covered with white plastic film or light-colored tarps to protect from weather and weighted down to prevent boards from being blown around by the wind.

Store above standing water.

Precautionary Statements

- **CAUTION:** Styrofoam™ Brand XPS Insulation is combustible. This product is combustible. Protect from high heat sources. A protective barrier or thermal barrier may be required as specified in the appropriate building code. For more information call the DuPont Contact Center at 866-583-2583 or contact your local building inspector. For emergencies contact Chemtrec 800-424-9300, CCN (Contract Number) 7442.
- Fabrication methods which involve cutting into this product may release the blowing agent(s) remaining in the cells. Provide adequate ventilation to assure localized concentrations in release areas are maintained below the lower flammable limit.
- If small particles are generated during further processing, handling or by other means, may form combustible dust concentrations in air. Mechanical cutting, grinding or sawing can cause formation of dusts. To reduce the potential for dust explosion, do not permit dust to accumulate.
- Rigid foam insulation does not constitute a working walkable surface or qualify as a fall protection product.

Supplemental Information

- The product meets the definition of an article and is exempt from US TSCA and Canadian DSL inventory requirements.

Compliant with Title 42 Chapter 85 Clean Air Act: Subchapter VII American Innovation and Manufacturing Act of 2020, and Section 612 US EPA Significant New Alternative Policy. Global Warming Potential <150. This product neither contains, nor was manufactured with a Class I or Class II ODS as defined by the U.S. Clean Air Act Section 602 (40 CFR 82, Subpt. A, App.A + B).

Compliant with CANADIAN ENVIRONMENTAL PROTECTION ACT, 1999, SOR/2016-137, 64.5 (1) Plastic foam or rigid foam product. Global Warming Potential <150.

Warning

- **WARNING: For Professional Use Only** - Read and follow the entire Safety, Handling, and Storage section carefully before use. The information below is designed to protect the user and allow for safe use and handling of DuPont products.

Due to the critical technical design aspects of many of its applications, DuPont recommends that qualified designers or consultants design your system. Follow all applicable federal, provincials, territories, local and employer regulations.



**For more information, visit us at
building.dupont.com
or call us at 1-833-338-7668**

NOTICE: No freedom from any patent owned by DuPont or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customers use and for ensuring that Customers workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries or regions. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY DUPONT. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. The buyer assumes all risks as to the use of the material. Buyers exclusive remedy or any claim (including without limitations, negligence, strict liability, or tort) shall be limited to the refund of the purchase price of the material. Failure to strictly adhere to any recommended procedures shall release DuPont de Nemours, Inc. or its affiliates of all liability with respect to the materials or the use thereof. The information herein is not intended for use by non-professional designers, applicators or other persons who do not purchase or utilize this product in the normal course of their business. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2025 DuPont. 43-D100064-enNA-1025 CDP.

Issue Date: 7/9/2025

Print Date: 7/31/2026